# SICHERT • BEFESTIGT • DICHTET • KLEBT



#### TECHNICAL INFORMATION

#### **BEST-KL 6006**

**BEST-KL 6006** is a one-component, solvent free and low viscous UVA-light curing adhesive based on a modified epoxy resin.

**BEST-KL 6006** is especially designed for bonding of synthetic materials and metals. It cures by exposure to UV-light with a wave length of 280-320nm. At least one of the bonding parts has to be permeable to UVA-light. The product is suitable for temperature and chemical resistant bonding of metals, synthetic materials and elastomers. In open applications the product features a dry surface after cure. It is also suitable for scratch resistant and flexible as well as chemical and temperature resistant casting of sensitive surfaces.

**BEST-KL 6006** combines high strength with good temperature and chemical resistance. Its low viscosity allows a good distribution on the adherents. Due to its capillary action it is also suitable for subsequent application.

### **PROPERTIES** (liquid product)

Chemical type Epoxy resin

Curing system UVA light

Appearance Colourless to whitish

Viscosity (Brookfield) 300 mPa·s

Density (DIN EN 542) 1,1 x 10<sup>3</sup>kg/m<sup>3</sup>

Shelf life 6 months

(Storage in unopened original container at 10°C up to 23°C)

Curing time @ RT (23°C)

Fixture time UVA-light 120 seconds

Functional strength UVA-light 120 seconds

Final strength 30 minutes

TI\_E\_KL6006\_Rev\_181026 Seite 1 von 2

# SICHERT • BEFESTIGT • DICHTET • KLEBT



## **STRENGTH VALUES (cured product)**

Tensile strength 32N/mm<sup>2</sup>

Elongation at break 10 %

Tensile shear strength (DIN EN 1465) glass/aluminum 20 Nmm²

Surface after cure dry

Appearance after cure Colorless to whitish

Temperature range -55°C - +150°C

### CHEMICAL AND ENVIRONMENTAL RESISTANCE

(DIN 53287 – Test in accordance with DIN EN 15865) In % of the initial strength after 1000h chemical absorption

Water/Glycol at 87°C 90 %

Motor oil (MIL-L-46 152) at 125°C 80%

Unleaded Gasoline at 23°C 80%

Brake fluid at 23°C 90%

1,1,1 trichlorethane at 23°C 90%

Ethanol at 23°C 90%

Acetone at 23°C 85%

For more information on resistance against other chemicals please contact BEST-Klebstoffe.

### **HEALTH AND SAFETY STANDARDS:**

Hazard Statements: May cause an allergic skin reaction. Harmful to aquatic life with long lasting effects. For further information please see corresponding material safety data sheets.

### **General**

The data and information above correspond to the current know-how of BEST-Klebstoffe GmbH & Co.KG. Our information and data have been developed from laboratory tests and extensive practical experience. It is the user's responsibility to perform receiving inspections and to determine suitability for the user's purpose of any production methods. We disclaim all warranties expressed or implied, that any product will have specific properties for a particular purpose. BEST-Klebstoffe GmbH & Co. KG reserves the right to change the contents of this document as necessary.

Revision: 181026 Revision Date: 26.10.2018

TI E KL6006 Rev 181026 Seite 2 von 2