



TECHNICAL INFORMATION

BEST-KL 6042

BEST-KL 6042 is a one-component, solvent free and low viscous UV-curing adhesive based on a modified epoxy resin.

BEST-KL 6042 is for bonding of glass with synthetic materials and metals. It cures by exposure to UVA-light with a wave length of 315 - 400 nm. At least one of the adherends has to be permeable to UVA-light. It is temperature- and chemical resistant after cure. The product features a dry surface after cure. It is especially suitable for a scratch resistant, flexible, chemical and temperature resistant casting of sensitive surfaces.

BEST-KL 6042 combines high strength with good temperature and chemical resistance. Its low viscosity allows a good distribution on the adherends.

PROPERTIES (liquid product)

Chemical type	Epoxy resin
Curing system	UVA light
Appearance	Colourless to whitish
Viscosity (Brookfield)	Approx. 300 mPa·s
Density (DIN 51757)	approx. 1,1 x 10 ³ kg/m ³
Shelf life (Storage in unopened original container at 10°C up to 23°C)	6 months
<u>Curing time @ RT (23°C)</u>	
Fixture time	120 seconds
Functional strength	120 seconds
Final strength	24 hours



STRENGTH VALUES (cured product)

Tensile strength (DIN 53504)	32N/mm ²
Elongation at break (DIN 53504)	10 %
Shear strength glass/aluminum	20 Nmm ²
Surface after cure	dry
Appearance after cure	Colourless to whitish
Temperature range	-55°C – +150°C

CHEMICAL AND ENVIRONMENTAL RESISTANCE
(DIN 53287 – Test in accordance with DIN 54454)

In % of the initial strength after 1000h chemical absorption

Water/Glycol at 87°C	90 %
Motor oil (MIL-L-46 152) at 125°C	80%
Unleaded Gasoline at 23°C	80%
Brake fluid at 23°C	90%
1,1,1 trichlorethane at 23°C	90%
Ethanol at 23°C	90%
Acetone at 23°C	85%

For more information on resistance against other chemicals please contact BEST-Klebstoffe.

HEALTH AND SAFETY STANDARDS:

Warning! May cause an allergic skin reaction. Harmful to aquatic life with long lasting effects. For further information please see corresponding material safety data sheets.

General

The data and information above correspond to the current know-how of BEST-Klebstoffe GmbH & Co.KG. Our information and data have been developed from laboratory tests and extensive practical experience. It is the user's responsibility to perform receiving inspections and to determine suitability for the user's purpose of any production methods. We disclaim all warranties expressed or implied, that any product will have specific properties for a particular purpose. BEST-Klebstoffe GmbH & Co. KG reserves the right to change the contents of this document as necessary.

Revision: 130529
Revision Date: 29.05.2013