

TECHNICAL INFORMATION

BEST-KL 6060

BEST-KL 6060 is a one-component, solvent free and medium viscous UVA-light curing adhesive based on a modified epoxy resin.

BEST-KL 6060 is suitable for the bonding of synthetic materials, glass, metals and elastomers. It cures by exposure to UVA-light with a wave length of 280 - 320 nm. At least one of the adherends has to be permeable to UVA-light. It is temperature- and chemical resistant after cure. The product features a dry surface after cure and is therefore predestined for the casting of components in the field of electronics.

BEST-KL 6060 combines high strength with good temperature and chemical resistance. It bridges gaps up to 1 mm, especially when subsequently exposing the excess adhesive.

PROPERTIES (liquid product)

Chemical type	Epoxy resin
Curing system	UVA light
Appearance	Colourless to whitish
Viscosity (Brookfield)	Approx. 1,000 mPa·s
Density (DIN EN 542)	approx. 1,1 x 10³kg/m³
Shelf life in unopened original (Storage temperature at 10°C up to 23°C)	6 months

CURING TIME @ RT (23°C)

Fixture time	120 seconds
Functional strength	120 seconds
Final strength	24 hours

**STRENGTH VALUES (cured product)**

Tensile strength	32N/mm²
Elongation at break	20 %
Tensile shear strength (DIN EN 1465) glass/aluminum	20 Nmm²
Tensile shear strength (DIN EN 1465) PC / PC	29 Nmm²
Surface after cure	dry
Appearance after cure	Colourless to whitish
Temperature range	-55°C – +150°C

CHEMICAL AND ENVIRONMENTAL RESISTANCE**(DIN 53287 – Test in accordance with DIN EN 15865)**

In % of the initial strength after 1000h chemical absorption

Water/Glycol at 87°C	90 %
Motor oil (MIL-L-46 152) at 125°C	80%
Unleaded Gasoline at 23°C	80%
Brake fluid at 23°C	90%
1,1,1 trichlorethane at 23°C	90%
Ethanol at 23°C	90%
Acetone at 23°C	85%

For more information on resistance against other chemicals please contact BEST-Klebstoffe.

HEALTH AND SAFETY STANDARDS:

Hazard Statements: May cause an allergic skin reaction. Harmful to aquatic life with long lasting effects. For further information please see corresponding material safety data sheets.

General

The data and information above correspond to the current know-how of BEST-Klebstoffe GmbH & Co.KG. Our information and data have been developed from laboratory tests and extensive practical experience. It is the user's responsibility to perform receiving inspections and to determine suitability for the user's purpose of any production methods. We disclaim all warranties expressed or implied, that any product will have specific properties for a particular purpose. BEST-Klebstoffe GmbH & Co. KG reserves the right to change the contents of this document as necessary.

Revision: 181026
Revision Date: 26.10.2018