

TECHNICAL INFORMATION

BEST-MK 1231

BEST-MK 1231 is a one-component, solvent-free, medium strength and medium viscous anaerobic curing adhesive based on di-methycrylate-ester with DVGW-certification.

BEST-MK 1231 is the standard product for securing of threads. It is also recommended for sealing of thread connections as well as pipe connections.

BEST-MK 1231 automatically spreads in the thread without leaking from the thread. The product provides a lubricating effect with the friction coefficient of an oiled screw. Disassembly is possible with special tools without causing damage to the thread.

PROPERTIES (liquid product)

Chemical Type Dimethacrylate ester

Curing system anaerobic

Colour blue

Strength medium

Viscosity (Brookfield) Sp. 4/100 RPM 1.5000 - 2.500 mPas/thix

@25°C

Density (DIN EN 542) $1.1 \times 10^{3} \text{ kg/m}^{3}$

Thread sizes all thread sizes

Thread friction 0,13

Shelf life in unopened original container 24 months

(Storage temperature 8 to 21°C)

Shelf life in unopened original BULK ca. 3 months

(Storage temperature 8 to 16°C)

Curing time @23°C

Fixture time 2 - 10 min.

Functional strength 2 - 3 hrs.

Total curing time 12 hrs.

TI_E_MK1231_Rev_180418 Seite 1 von 2





STRENGTH VALUES (cured product)

Compression/shear strength (DIN EN 15337) 16 N/mm²

Breakloose Moment (DIN EN 15865) 16 Nm

Breakaway Moment (DIN EN 15865) 10 Nm

Temperature range -60°C to +150°C

CHEMICAL AND ENVIRONMENTAL RESISTANCE

(DIN 53287 - Test in accordance with DIN EN 15865)

in % of the initial strength after 1000h chemical absorption

Water/Glycol at 87°C 85%

Motor Oil (MIL-L-46 152) at 125°C 95%

Unleaded Gasoline at 23°C 95%

Brake fluid at 23°C 100%

1,1,1 Trichlorethane at 23°C 95%

Ethanol at 23°C 85%

Acetone at 23°C 90%

For more information on resistance against other chemicals please contact BEST-Klebstoffe.

HEALTH AND SAFETY STANDARDS

This product is not classified as dangerous according to regulation (EC) 1272/2008. General rules regarding handling of chemicals apply. For further information please see corresponding material safety data sheets.

GENERAL

The data and information above correspond to the current know-how of BEST-Klebstoffe GmbH & Co. KG. Our information and data have been developed from laboratory tests and extensive practical experience. They shall not release any customer from the duty to perform receiving inspections and to do test runs in view of any intended use, nor do they constitute a representation that any product will have specific properties or be suitable for any definite use. BEST-Klebstoffe GmbH & Co. KG reserves the right to chance the contents of this as necessary.

Revision: 180418

Revision date: 18.04.2018

TI E MK1231 Rev 180418 Seite 2 von 2