



## TECHNICAL INFORMATION

### BEST-MK 2338

**BEST-MK 2338** is a one-component, solvent-free, high strength, and high viscous anaerobically curing adhesive based on di-methacrylate-ester.

**BEST-MK 2338** is specially designed for fastening of coaxial adherends, e.g. bearings, bushings and shaft-/hub connections. Another field of application is the securing and sealing of pipe- and thread connections and the sealing of surfaces, especially in the field of hydraulics. As a sealing for metal thread connections BEST-MK 2338 withstands pressure up to 65 bar (see test report DVGW AZ: 04/327/5146/1).

**BEST-MK 2338** automatically spreads in the thread without leaking from the thread. Disassembly is not feasible without the possibility of damaging screw or thread.

#### PROPERTIES (liquid product)

Chemical type	Di-methacrylate-ester
Curing system	Anaerobic
Appearance	green
Strength class	high
Viscosity (Brookfield)	8.000 mPas/thix
Density (DIN 51757)	1,1 x 10 <sup>3</sup> kg/m <sup>3</sup>
Thread size	up to R3"
Max. gap filling	0,1 – 0,25 mm
Thread friction	0,17
Shelf life <small>(Storage in unopened original container at 10°C up to 23°C)</small>	12 months
<u>Curing time @23°C</u>	
Fixture time	3 to 10 minutes
Functional strength	2 – 4 hours
Final strength	12 hours



**STRENGTH VALUES (cured product)**

Compression shear strength (DIN 54452)	25 N/mm <sup>2</sup>
Breakloosemoment (DIN 54454)	31 Nm
Breakawaymoment (DIN 54454)	36 Nm
Pressure before leakage (test report DVGW-reference number: 04/327/5146/1)	65 bar

**TEMPERATURE RANGE** -60°C – +150°C

**CHEMICAL AND ENVIRONMENTAL RESISTANCE**  
**(DIN 53287 – Test in accordance with DIN 54454)**

in % of the initial strength after 1000h chemical absorption

Water/Glycol at 87°C	90 %
Motor oil (MIL-L-46 152) at 125°C	100%
Unleaded Gasoline at 23°C	95%
Brake fluid at 23°C	95%
1,1,1 trichlorethane at 23°C	95%
Ethanol at 23°C	100%
Acetone at 23°C	95%

For more information on resistance against other chemicals please contact BEST-Klebstoffe.

**HEALTH AND SAFETY STANDARDS**

This product is not classified as dangerous according to regulation (EC) 1272/2008. General rules regarding handling of chemicals apply. For further information please see corresponding material safety data sheets.

**General**

The data and information above correspond to the current know-how of BEST-Klebstoffe GmbH & Co.KG. Our information and data have been developed from laboratory tests and extensive practical experience. It is the user's responsibility to perform receiving inspections and to determine suitability for the user's purpose of any production methods. We disclaim all warranties expressed or implied, that any product will have specific properties for a particular purpose. BEST-Klebstoffe GmbH & Co. KG reserves the right to change the contents of this document as necessary.

Revision: 130524  
Revision Date: 24.05.2013